

# Longcester® P 5713-2

# **Product Data Sheet**

# Saturated, carboxylated polyester resin

## General Description

P 5713-2 is a medium reactivity polyester resin, designed for 93:7 TGIC curing powder coatings. Coatings based on it exhibit:

- · Good flow
- · Outstanding mechanical properties
- · Excellent outdoor durability
- · Good yellowing resistance

## Extrusion & Application Conditions

Extruder: Lingyu SLI-25
Zone I temp.: 85~105 °C
Zone II temp.: 100~120 °C
Screw speed: 400~500rpm

Panel: 0.5mm pre-treated cold-rolled steel

Spray gun: Lingyu SJ-5 Voltage: 60~90kV

Curing cycles: 10 min. @  $200^{\circ}$ C; 15 min. @  $180^{\circ}$ C

#### Packaging

- · White PE bag, N.W.25kg/bag, 1000kg/pallet.
- · Big bags 750 kg.

#### Storage

Product Specifications			
Property	Range	Test Method	
Appearance	Pale granules	Visual	
Acid value	30~36 mg KOH/g	ASTM D1639	
Viscosity	4000~6000 mpa.s	ASTM D4287	
Color	max.2	ASTM D1544	
Tg	approx. 64	DSC	

Starting Formulation		
Component	Weight	
P 5713-2	558.0	

 LC- TGIC
 42.0

 Titanium dioxide
 300.0

 LC-88 Flow agent
 9.0

 Benzoin
 4.5

Film Properties				
Item	Result	Test Method		
Film thickness, µm	approx. 60	ASTM D1186		
Gloss @ 60°, %	min. 90	ASTM D523		
Direct/reverse impact, inch lbs	160/160	ASTM D2794		
1/8" Conical mandrel	pass	ASTM D522		
Adhesion(cross cut)	5B	ASTM D3359		
Pencil hardness	Н	ASTM D3363		

### Yantai Longcai Advanced Materials Co., Ltd

No.18 Hangzhou Road., Haiyang Development Zone, Yantai, China T Post code: 265100 V

Tel.: +86 535-330 6639 Web-site: www.longcester.com Fax: +86 535-330 6828 E-mail: info@longcester.com

Disclaimer: The information given in this sheet is based on our present research and is believed reliable, but it is solely the user's responsibility to confirm by testing for its specific use. LONGCAI MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.