

Longcester[®] P 5040 Saturated, carboxylated polyester resin

Product Data Sheet

General Description

Dead-matt gloss effect resin, for architectural purposes.

- $\cdot \, \text{Excellent}$ outdoor durablity
- \cdot Medium reactivity
- $\cdot \mbox{Suitable}$ for dead matte gloss application

·Flow and mechanical performance balance

Extrusion & Application Conditions

Lingyu SLJ-20

400~500rpm

Lingyu SJ-5

10 min. @ 200℃

60~90kV

0.7mm pre-treated cold-rolled steel

85~105℃ **100~120**℃

Product Specifications		
Property	Range	Test Method
Appearance	clear granule	Visual
Viscosity	25~35 pa.s	ASTM D4287
Acid value	5~10 mg KOH/g	ASTM D1639
Color	Max 2	ASTM D1544
Тg	appr. 62	DSC

Starting Formulation		
Component	Weight	
P 5040	60.0	
LC-TGIC	1.0	
Titanium dioxide	37.7	
LC-88 Flow agent	1.0	
Benzoin	0.3	

Packaging

Extruder:

Zone I temp.:

Zone II temp.:

Screw speed: Panel:

Spray gun:

Voltage: Curing cycles:

- \cdot White PE bag, N.W.25kg/bag, 1000kg/pallet.
- · Big bags 750 kg

Storage

The product can be stably stored for at least one year when kept in closed containers in a dry place at temperature below 30 $^\circ\!\mathrm{C}$. Avoid exposure to direct sunlight.

Film Properties		
Item	Result	Test Method
Film thickness, μm	approx. 60	ASTM D1186
Gloss @ 60º, %	max. 6 unit	ASTM D523
Direct/reverse impact, inch lbs	80/80	ASTM D2794
1/8" Conical mandrel	pass	ASTM D522
Adhesion(cross cut)	5B	ASTM D3359
Pencil hardness	Н	ASTM D3363

Yantai Longcai Advanced Materials Co., Ltd					
No.18 Hangzhou Road., Haiyang Development Zone, Yantai, China	Tel.: +86 535-330 6639	Fax: +86 535-330 6828			
Post code: 265100	Web-site: www.longcester.com	E-mail: info@longcester.com			

Disclaimer: The information given in this sheet is based on our present research and is believed reliable, but it is solely the user's responsibility to confirm by testing for its specific use. LONGCAI MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.