

## Longcester<sup>®</sup> LC-3329

### Exterior Matting Agent for Powder Coatings

#### General Description

LC-3329 is a highly efficient matting additive for hybrid and exterior powder coatings. Highly matting efficiency.

- Not affect film mechanical properties
- Excellent yellowing resistance
- Excellent weather resistance
- Recommended levels:1~4% (total formulation)

#### Product Specifications

Property	Range	Test Method
Appearance	Light yellow powder	Visual
Particle size distribution(D50)	600 micron	ISO 3001
Melting Range ( °C )	109~117	ISO11357-1
Volatile	<1.0%	Longcai method

#### Packaging

- White PE bag, N.W.25kg/bag

#### Storage

The product can be stably stored for at least one year when kept in closed containers in a dry place at temperature below 30 °C .  
Avoid exposure to direct sunlight.